







Typical spun yarn properties



Technical Bulletin 360904

1.5dtex 38m



Ingeo Worldwide Offices
Amsterdam, Hong Kong, London,
Milan, Minneapolis, New York and Tokyo



www.ingeofibers.com

Contact

1 800 66 INGEO (USA only)
+1 989 633 1746 (Worldwide)

Ingeo and the EcoPLA design are trademarks of NatureWorks LLC © 2005
15305 Minnetonka Blvd., Minnetonka MN 55345
GSFIB036090305V2

No freedom from any patent of NatureWorks LLC or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, NatureWorks customers are responsible for determining whether the products and information in this document are appropriate for the customer's use and for ensuring that the customer's workplace and disposal practices are in compliance with applicable laws and regulations. NatureWorks assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN: ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.